

MK20 32 cell 300mm Material Specification Sheet

Material Composition					
	Range in %			Range in %	
Alumina Oxide	28-38		Titanium Oxide	0-1	
Silicon Dioxide	45-55		Calcium Oxide	0-1	
Iron Oxide	0.5-1.5		Magnesium Oxide	8-10	
			Sodium Oxide	0-0.5	
			Potassium Oxide	0.5-2	

Physical and Chemical Characteristics						Resulting characteristic parameters		
	Nominal	Range		Range	unit		Nominal	unit
Cell Size	3.8 mm	±10%	Porosity ¹	7-12%		Active Surface	724	m ² /m ³
Wall Thickness	0.8 mm	±10%	Thermal Expansion ²	2-3	x10 ⁻⁶ °K ⁻¹	Specific Heat ³	810	J/kgK
Open Frontal Area	66%	±10%	Solid Density	1,9-2,1	g/cm ³			

Dimensions					
	Nominal	Range		Nominal	Range
Height	300 mm	±3 mm	7 block stack width	1057	±2%
Width	150 mm	±3 mm	weight per volume	0.680 g/cm ³	±12%
Length	150 mm	±3 mm	# of channels	1024	

Notes

- 1) Method Used - water absorption
- 2) technical CTE at 800°C
- 3) 100 degrees C